

Luban HP5105R

Polypropylene Homopolymer



Description

Luban HP5105R is manufactured using the Spheripol Technology. Luban HP5105R is a homopolymer polypropylene formulated with an anti-gas fading stabilization package. Luban HP5105R is used for the production of (bulk) continuous filaments (BCF/CF) and fine denier staple fibers.

Application

BCF: Residential carpets, object carpets, carpets for automotive.
CF: Fabrics for mattress covers, POY for socks, clothes, inlets for suitcases.

Properties (Typical Values)

Property	Units	Test method	Value
Melt flow rate (230°C/2.16 kg)	g/10 min	ISO 1133	25
Density	g /cm ³	ISO 1183	0.90
Tensile modulus (1 mm/min)	MPa	ISO 527-2	1500
Tensile stress at yield (50 mm/min)	MPa	ISO 527-2	34
Tensile strain at yield (50 mm/min)	%	ISO 527-2	11
Tensile strain at break (50 mm/min)	%	ISO 527-2	> 50
Charpy notched impact strength (+23°C)	kJ/m ²	ISO 179/1eA	4
Heat Deflection Temperature (0.45 MPa)	°C	ISO 75-2	85
Vicat Softening Temperature	°C	ISO 306-A	134

Note: These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

Processing Guidelines

The Typical Processing Conditions for Luban HP5105R are:

Extrusion Temperatures	210 – 240 °C
Rolls Temperature	80 – 120 °C
Quenching Temperature	10 – 20 °C
Draw Ratio	2.8 – 3.3
Texturising Temperature	150 – 170 °C

Note: Processing parameters should only be used as guidelines. The above properties values are not to be construed as specifications.

Luban HP5105R

Polypropylene Homopolymer



Storage and Handling

Luban HP5105R must be protected from direct sunlight and should be stored in a shaded and completely dry area. During handling and processing, the material should be kept in a well-ventilated area to prevent the accumulation of dust and fumes. Contact with strong oxidizers, excessive heat, sparks or open flame should be avoided as this could initiate the degradation process and consequently impact the quality of the material.

Safety

Luban HP5105R is not classified as dangerous preparation. For further information about safety in handling and processing please refer to the Safety Data Sheet.

Food Contact

Luban HP5105R meets the requirements of the U.S. Food and Drug Administration (FDA) as specified in 21 CFR 177.1520, covering safe use of polyolefin articles and components of articles intended for direct food contact. For additional information on approved conditions of use for food contact applications, please refer to the "Product Stewardship Declaration".

Recycling

The product is suitable for recycling using modern methods of shredding and cleaning. In-house production waste should be kept clean to facilitate direct recycling.

Updated: March. 2023

Disclaimer:

Values given here are typical and should not be interpreted as specification. Before using OQ product, customers and other users should make their own independent determination that the product is suitable for the intended use. This document does not constitute a warranty, express or implied, including a warranty of merchantability or fitness for a particular purpose. In addition, no immunity under OQ or third parties' intellectual property rights shall be implied from this document. No one is authorized to make any warranties, issue any immunities or assume any liabilities on behalf of OQ except in a writing signed by an authorized OQ employee. Unless otherwise agreed in writing, the exclusive remedy for all claims is replacement of the product or refund of the purchase price at OQ's option, and in no event shall OQ be liable for special, consequential, incidental, punitive or exemplary damages.

OQ head office
PO Box 281, PC 118
Musecat Grand Mall,
Musecat, Sultanate of Oman
www.oq.com

 **Media Kimia**
industries
www.mediakimia.com

أوكيو المكتب الرئيسي
مندوقة بريد ٢٦١، الرمز البريدي ١١
مسقط جرائد مول
سلطنة عمان، مسقط
www.oq.com